

# Top Shape®

HILLYARD  
**TRILOGY**  
SYSTEM I

A quality, acrylic copolymer floor polish formulated to provide a clear, wet-look, protective shine on your floors. Top Shape's advanced formula is perfect for resilient tile, terrazzo, unglazed ceramic, quarry tile, paver brick, natural stone, sealed wood, or concrete flooring.

## Features & Benefits

- 18% solids clear acrylic copolymer for enhanced appearance.
- Self-leveling for easy application.
- Minimum maintenance required.

## Directions

**PREPARATION:** Strip other finishes from the floor with Hillyard Devastator or Power-Strip following label directions. Use floor machine with black pad or brush (do not use abrasive pads on tile containing asbestos). Remove stripping solution with a wet vacuum. Heavy rinse with Hillyard Nutra-Rinse mixed 4 oz. per gallon of water and pick up with the wet vacuum. Damp mop all flooring twice with clean, cool water. Allow the floor to dry.

**APPLICATION:** When using a sealer, apply a minimum of 5 coats of Top Shape with a clean synthetic mop. Allow each coat to dry a minimum of 30 minutes before applying the next. When a sealer is not used, apply a minimum of 7 coats of Top Shape.

**NOTE:** Allow for longer dry time between coats of finish if the humidity is above 80% or the floor temperature is below 60°F (16°C).

**MAINTENANCE:** Use a Hillyard Super Hil-Tone treated dust mop daily to remove loose dirt and grit. Damp mop or autoscrub as scheduled with Hillyard Super Shine-All, Top Clean, or Arsenal Heavy Duty Floor Cleaner. After the floor has been cleaned, gloss may be restored by spray buffing with Hillyard Hil-Glo. Scrub and recoat as scheduled with a minimum of 2 coats of Top Shape.

**FLOOR PAD RECOMMENDATIONS:** **Strip** - black; **Spray Buff** - red followed by white; **Scrub and Recoat** - blue or green; **Autoscrubbing** - red.

**NOTICE:** Do not use an ammoniated cleaner for daily care. If the floor is very porous, seal with Hillyard Hil-Tex+, Seal 340 or Seal 341 before applying Top Shape. If stains are a problem, seal with Strong Guard. Do not pour unused finish or seal back into the original container.

**High Speed Burnishing:** Because high speed burnishing is affected by many variables, including equipment type, pad pressure, frequency of burnishing, and traffic loads contact Hillyard Technical Service for pad recommendations.

## Certifications, Registrations & Notes

Classified by Underwriters Laboratories, Inc.® as to slip resistance. (1865).



## Safety

See material safety data sheet and product label for safety information, handling and proper use.

## HMIS

	Concentrate
Health	0
Flammability	0
Reactivity	0

## Technical Specifications

Color	White
Scent	Non-Objectionable
Appearance	Milky Emulsion
pH (concentrate)	8.00 - 9.00
Non-Volatile Matter	18.00%
Dilution Rate	RTU

## Availability

Item	Pack
HIL0052206	4 - 1 Gallon Containers
HIL0052207	1 - 5 Gallon Bag-In-Box
HIL0052209	1 - 55 Gallon Drum

**Coverage Rates:** 1,500 - 2,000 Sq. Ft. per Gallon  
*Rates can vary greatly based on surface and application method.*

HILLYARD

P.O. Box 909  
St. Joseph, MO 64502  
1-800-365-1555  
www.hillyard.com